

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
31 July 2003 (31.07.2003)


PCT

(10) International Publication Number
WO 03/062491 A2

- (51) International Patent Classification⁷: C23C 26/00
- (21) International Application Number: PCT/US03/01825
- (22) International Filing Date: 22 January 2003 (22.01.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/351,555 24 January 2002 (24.01.2002) US
- (71) Applicant: H. C. STARCK INC. [US/US]; 45 Industrial Place, Newton, MA 02161-1951 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): AIMONE, Paul, R. [US/US]; 20 Tanglewood Drive, Bridgewater, MA 02324-2275 (US). KUMAR, Prabhat [US/US]; 31 Pinewood Drive, Framingham, MA 01701-7656 (US). JEPSON, Peter, R. [US/US]; 21 Marsh Avenue, Newbury, MA 01951-2402 (US).
- (74) Agents: VAN EYL, Diderico et al.; Bayer Corporation, 100 Bayer Road, Pittsburgh, PA 15205-9741 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— without international search report and to be republished upon receipt of that report

[Continued on next page]

(54) Title: REFRACTORY METAL AND ALLOY REFINING BY LASER FORMING AND MELTING



Sample 1
Sample 2
Sample 3
Sample 4
Sample 5

(57) Abstract: A process to chemically refine and consolidate tantalum, niobium and their alloys to a fabricated product of net shape or near-net shape with higher throughput, more consistency, and lower manufacturing costs compared to prior art routes or rejuvenate damaged and deteriorated refractory metal parts. Powder metal is loaded into hoppers to be fed into laser forming/melting equipment. A suitable substrate is loaded into a laser forming/melting chamber onto which the powder will be deposited and consolidated in a point-scan process. As the powder is fed onto successive points of the surface of the substrate in linear traces, the laser is used to heat and partially melt the substrate and completely melt the powder. A combined deposition and melt beam traces the substrate surface repeatedly over a selected area to build up a dense coating of controlled microstructure in multiple layers. A fully dense deposit is built up that becomes the desired shape.

BEST AVAILABLE COPY

WO 03/062491 A2